PRODUCT DATA

Bostik® DRICOTE® Blade & Bit Cutting Lubricant

Porties DRICOTE Blade & Bis/Curting Labrican *For Cleaner, There Cans of Weal Laminares & Metal Reducer, Scan Bull-age Reducer, Commission Reducer, Scan Bull-age Reduc

Date of Last Revision: 02/06/06

Product Description

Regular use of Bostik® DriCote® on saw blades, router and drill bits and knives significantly reduces cutting friction and the buildup of resin or pitch.

DriCote dries in seconds and will not gum-up, even after several applications.

Product Benefits

- Prevents resin buildup. Reduces blade cleanings.
- Extends overall life of blades and bits by up to 3 times!
- More than doubles time between resharpenings.
- Contains NO silicone or petroleum oil. Will NOT stain wood or interfere with glues or finishes.
- Reduces cutting friction and heat by 30%.
- Prolongs equipment life by reducing saw or drill motor drag by up to 25%.
- Increases productivity by less downtime for saw blade changeovers.
- Works equally well on steel or carbide, stellite and diamond-tipped cutting blades.
- Environmentally safer aerosol—NO CFCs and NO ODCs.

Directions

To Reduce Friction and Pitch Buildup:

Clean blade or bit with a degreasing agent (lacquer thinner). Spray a thin, even coat over the entire blade or bit, including the gullets and especially the cutting edge. Allow a few seconds to dry.

For Best Results:

After several cuts, re-spray entire blade or bit. Reapply daily or more frequently based on workload and material being cut.

Applications

Wood Working

- Saw blades
- Router bits
- Drill bits
- Jointers
- Planers
- Edgers
- Screws & nails

Other

- Paper cutters & drills
- Bindery knives
- Shears
- Chains
- Pulleys
- Gears
- Sliding glass door tracks

Product Specifications

Container	Net	Case	Case
	Weight	Pack	Weight
Aerosol	10.75 oz.	12	12.2 lbs.

Bostik, Inc.

211 Boston Street Middleton, MA 01949-2128 USA TEL. 888-603-8558 FAX 978-750-7293 http://www.bostik-us.com

IMPORTANT NOTICE

All statements, technical information and recommendations set forth herein are based on tests which Bostik, Inc. believes to be reliable. However, Bostik does not guarantee their accuracy or completeness. The buyer should conduct its own tests of this product before use to determine proper preparation technique and suitability for proposed application. Any sales of this product shall be on terms and conditions set forth on BostikFindley's order acknowledgment. Bostik, Inc. warrants that the product conforms with Bostik written specifications, and is free from defects. BOSTIK, INC. DISCLAIMS ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING THE WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. THE BUYER'S SOLE REMEDY FOR NONCOMPLIANCE WITH THIS WARRANTY SHALL BE FOR THE REPLACEMENT OF THE PRODUCT OR REFUND OF THE BUYER'S PURCHASE PRICE. IN NO CASE WILL BOSTIK BE LIABLE FOR DIRECT, CONSEQUENTIAL ECONOMIC OR OTHER DAMAGES.